

Interval reviewed and revised on September 24, 2015, by Nyssa Moore as per ABSA AB-506, Section 11.4.3 Interval Revisions. Interval to be re-assigned at GR.2 (120 months) for Cryogenic Vessels as per AB-506 Edition 2, Rev. 7 based on the most recent inspection performed. Technical basis to support includes:

- No significant visual external or internal findings on most recent inspection

- No relevant WFMPI findings left behind during most recent inspection

- All UT readings found to be above nominal thicknesses or within the rules of API 510 7.4.3 Evaluation of Pitting and may be ignored due to being widely scattered in as well as believed to be from construction and not active corrosion mechanisms.

A handwritten signature in black ink, appearing to be 'N. Moore', located at the bottom right of the page.